

# Test Report

Report No. SCL01I095665001

Page 1 of 5

**Applicant** DONGGUAN IN MEI COATING CO.,LTD

**Address** TIANXIN AREA,HUANGJIANG TOWN,DONGGUAN CITY,GUANGDONG PROVINCE

**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client**

Sample Name	INK
Part No.	G432
Color	10400
Sample Received Date	Oct. 25, 2016
Testing Period	Oct. 25, 2016 to Oct. 28, 2016

**Test Conducted:**

As requested by the applicant, for details refer to next page(s)

Tested by

*Frank Zhang*

Reviewed by

*Cathy Huang*

Approved by

*Danny Liu*

Date

Oct. 28, 2016

Danny Liu

Technical Manager

No. R158921375

Centre Testing International Group Co.,Ltd.

Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

# Test Report

Report No. SCL01I095665001

Page 2 of 5

## Executive Summary:

### TEST REQUEST

European Standard on Safety of Toys

- EN 71-3:2013+A1:2014 Migration of certain elements

### CONCLUSION

**PASS**

\*\*\*\*\* For Further Details, Please Refer To the Following Page(s) \*\*\*\*\*

# Test Report

Report No. SCL01I095665001

Page 3 of 5

## European Standard on Safety of Toys

### ▼ EN 71-3:2013+A1:2014 Migration of certain elements

Method(s) EN 71-3:2013+A1:2014 was/were used, and the item(s) was/were determined by ICP-OES, ICP-MS, HPLC-ICP-MS and/or GC-MS.

### Category III: scraped-off toy material

<u>Tested Item(s)</u>	<u>Result (mg/kg)</u>	<u>MDL (mg/kg)</u>	<u>Limit (mg/kg)</u>
Aluminium (Al)	N.D.	50	70000
Antimony (Sb)	N.D.	5	560
Arsenic (As)	N.D.	5	47
Barium (Ba)	N.D.	50	18750
Boron (B)	N.D.	50	15000
Cadmium (Cd)	N.D.	1	17
Chromium (III) <sup>#1</sup>	N.D.	0.2	460
Chromium (VI)	N.D.	0.002	0.2
Cobalt (Co)	N.D.	5	130
Copper (Cu)	N.D.	50	7700
Lead (Pb)	N.D.	5	160
Manganese (Mn)	N.D.	50	15000
Mercury (Hg)	N.D.	5	94
Nickel (Ni)	N.D.	5	930
Selenium (Se)	N.D.	5	460
Strontium (Sr)	N.D.	50	56000
Tin (Sn) <sup>#2</sup>	N.D.	2	180000
Organic tin (TBT) <sup>#3</sup>	N.D.	0.05	12
Zinc (Zn)	N.D.	50	46000

# Test Report

Report No. SCL01I095665001

Page 4 of 5

**Remark:**

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million
- Filter paper was used instead of membrane filter in lab testing.
- <sup>#1</sup> Trivalent chromium (Cr (III)) = Chromium (Cr) - Hexavalent chromium (Cr (VI)) , where the chromium content exceeded the limits of hexavalent chromium and/or trivalent chromium, then hexavalent chromium was analyzed by HPLC-ICP-MS and trivalent chromium content was calculated using the formula.
- <sup>#2</sup> Tin (Sn) content can be used for screen test for organic tins analysis to show compliance with the requirement of EN 71-3:2013+A1:2014.
- <sup>#3</sup> The migration of organic tin is expressed as tributyltin (TBT). where the tin content exceeded the limit of organic tin, ten organic tins listed in table were determined by GC-MS and the client should be noted there are other organic tins may be present in toy materials.

Organic tins tested under EN 71-3:2013+A1:2014
Methyl tin (MeT)
Butyl tin (BuT)
Dibutyl tin (DBT)
Tributyl tin (TBT)
Tetrabutyl tin (TeBT)
n-Octyl tin (MOT)
Di-n-octyl tin (DOT)
Di-n-propyl tin (DProT)
Diphenyl tin (DPhT)
Triphenyl tin (TPhT)

**Tested Sample/Part Description**

White ink

# Test Report

Report No. SCL01I095665001

Page 5 of 5

## Photo(s) of the sample(s)



\*\*\* End of Report \*\*\*

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of CTI, this report can't be reproduced except in full.