

# Test Report

Report No. SCL011004084006

Page 1 of 6

**Applicant** DONGGUAN IN MEI COATING CO.,LTD

**Address** TIANXIN AREA,HUANGJIANG TOWN,DONGGUAN CITY,GUANGDONG PROVINCE

**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client**

Sample Name	INK
Part No.	G432(PB)
Sample Received Date	Jan. 19, 2016
Testing Period	Jan. 19, 2016 to Jan. 22, 2016

**Test Conducted:**

As requested by the applicant, for details refer to next page(s)

Tested by

Reviewed by



Danny Liu  
Technical Manager

Date

Jan. 22, 2016

al Group Co.,Ltd.

Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

No. R158929881

# Test Report

Report No. SCL011004084006

Page 2 of 6

## Executive Summary:

### TEST REQUEST

(1)ASTM F963-11 Standard Consumer Safety Specification for Toy Safety

- Clause 4.3.5 Heavy elements – Migration of certain elements

(2)European Standard on Safety of Toys

- EN 71-3:2013+A1:2014 Migration of certain elements

### CONCLUSION

**PASS**

**PASS**

\*\*\*\*\* For Further Details, Please Refer To the Following Page(s) \*\*\*\*\*

# Test Report

Report No. SCL011004084006

Page 3 of 6

## 1) ASTM F963-11 Standard Consumer Safety Specification for Toy Safety

### ▼ Clause 4.3.5 Heavy elements – Migration of certain elements

Method(s) ASTM F963-11 Clause 8.3 was/were used, and the item(s) was/were analyzed by ICP-OES.

<u>Tested Item(s)</u>	<u>Result</u> (mg/kg)	<u>MDL</u> (mg/kg)	<u>Limit</u> (mg/kg)
Soluble Antimony (Sb)	N.D.	5	60
Soluble Arsenic (As)	N.D.	2.5	25
Soluble Barium (Ba)	16	5	1000
Soluble Cadmium (Cd)	N.D.	5	75
Soluble Chromium (Cr)	N.D.	2.5	60
Soluble Lead (Pb)	N.D.	5	90
Soluble Mercury (Hg)	N.D.	2.5	60
Soluble Selenium (Se)	N.D.	5	500

#### Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million
- Results shown of soluble elements are of adjusted analytical results by subtracting analytical Correction factor
- Filter paper was used instead of 0.45µm membrane filter in lab testing.

# Test Report

Report No. SCL011004084006

Page 4 of 6

## 2) European Standard on Safety of Toys

### ▼ EN 71-3:2013+A1:2014 Migration of certain elements

Method(s) EN 71-3:2013+A1:2014 was/were used, and the item(s) was/were determined by ICP-OES, ICP-MS, HPLC-ICP-MS and/or GC-MS.

### Category III: scraped-off toy material

Tested Item(s)	Result (mg/kg)	MDL(mg/kg)	Limit(mg/kg)
Aluminium (Al)	68	50	70000
Antimony (Sb)	N.D.	5	560
Arsenic (As)	N.D.	5	47
Barium (Ba)	N.D.	50	18750
Boron (B)	N.D.	50	15000
Cadmium (Cd)	N.D.	1	17
Chromium (III) <sup>#1</sup>	N.D.	0.2	460
Chromium (VI)	N.D.	0.002	0.2
Cobalt (Co)	N.D.	5	130
Copper (Cu)	N.D.	50	7700
Lead (Pb)	N.D.	5	160
Manganese (Mn)	N.D.	50	15000
Mercury (Hg)	N.D.	5	94
Nickel (Ni)	N.D.	5	930
Selenium (Se)	N.D.	5	460
Strontium (Sr)	N.D.	50	56000
Tin (Sn) <sup>#2</sup>	N.D.	2	180000
Organic tin (TBT) <sup>#3</sup>	N.D.	0.05	12
Zinc (Zn)	N.D.	50	46000

# Test Report

Report No. SCL011004084006

Page 5 of 6

**Remark:**

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million
- Filter paper was used instead of membrane filter in lab testing.
- <sup>#1</sup> Trivalent chromium (Cr (III)) = Chromium (Cr) - Hexavalent chromium (Cr (VI)) , where the chromium content exceeded the limits of hexavalent chromium and/or trivalent chromium, then hexavalent chromium was analyzed by HPLC-ICP-MS and trivalent chromium content was calculated using the formula.
- <sup>#2</sup> Tin (Sn) content can be used for screen test for organic tins analysis to show compliance with the requirement of EN 71-3:2013+A1:2014.
- <sup>#3</sup> The migration of organic tin is expressed as tributyltin (TBT). where the tin content exceeded the limit of organic tin, ten organic tins listed in table were determined by GC-MS and the client should be noted there are other organic tins may be present in toy materials.

Organic tins tested under EN 71-3:2013+A1:2014
Methyl tin (MeT)
Butyl tin (BuT)
Dibutyl tin (DBT)
Tributyl tin (TBT)
Tetrabutyl tin (TeBT)
n-Octyl tin (MOT)
Di-n-octyl tin (DOT)
Di-n-propyl tin (DProT)
Diphenyl tin (DPhT)
Triphenyl tin (TPhT)

**Tested Sample/Part Description**

White ink