

Report No. SCL01I00408400701

Page 1 of 6

Applicant ZHANGZHOU YINMEI PRINTING INK CO., LTD

Address DONGCHE VILLAGE , HUOTIAN TOWN, YUNXIAO COUNTY, ZHANGZHOU

CITY, FUJIAN PROVINCE, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name INK

Client Reference Information G003(PVA), G004(PVAN)

Sample Received Date Jan. 19, 2016

Testing Period Jan. 19, 2016 to Jan. 22, 2016

#### **Test Conducted:**

As requested by the applicant, for details refer to next page(s)

Tested by

Reviewed by

Date

Jan. 22, 2016

Danny Liu
Technical Manager

No. R158929881

Group Co.,Ltd. Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

Hotline: 400-6788-333 www.cti-cert.com E-mail: info@cti-cert.com Complaint call: 0755-33681700 Complaint E-mail: complaint@cti-cert.com



Report No. SCL01I00408400701

Page 2 of 6

## **Executive Summary:**

TEST REQUEST	CONCLUSION
--------------	------------

(1) ASTM F963-11 Standard Consumer Safety Specification for Toy Safety

- Clause 4.3.5 Heavy elements – Migration of certain elements PASS

(2) European Standard on Safety of Toys EN 71-3:2013+A1:2014 Migration of certain elements \*\*\*\*\*\* For Further Details, Please Refer To the Following Page(s) \*\*\*\*\*\*\*\*\*



Report No. SCL01I00408400701

Page 3 of 6

### 1) ASTM F963-11 Standard Consumer Safety Specification for Toy Safety

### **▼**Clause 4.3.5 Heavy elements – Migration of certain elements

Method(s) ASTM F963-11 Clause 8.3 was/were used, and the item(s) was/were analyzed by ICP-OES.

			15, 107	
Tested Item(s)	Result (mg/kg)		MDL (mg/kg)	Limit (mg/kg)
Soluble Antimony (Sb)	N.D.		5	60
Soluble Arsenic (As)	N.D.	130	2.5	25
Soluble Barium (Ba)	16	(6)	5	1000
Soluble Cadmium (Cd)	N.D.		5	75
Soluble Chromium (Cr)	N.D.		2.5	60
Soluble Lead (Pb)	N.D.		5	90
Soluble Mercury (Hg)	N.D.		2.5	60
Soluble Selenium (Se)	N.D.		5	500

#### Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million
- Results shown of soluble elements are of adjusted analytical results by subtracting analytical Correction factor
- Filter paper was used instead of 0.45μm membrane filter in lab testing.
- The test result(s) is(are) presented in reference to the result(s) that reported in SCL01I004084007.



Hotline: 400-6788-333 www.cti-cert.com E-mail: info@cti-cert.com Complaint call: 0755-33681700 Complaint E-mail: complaint@cti-cert.com



Report No. SCL01I00408400701

Page 4 of 6

### 2) European Standard on Safety of Toys

## **▼**EN 71-3:2013+A1:2014 Migration of certain elements

Method(s) EN 71-3:2013+A1:2014 was/were used, and the item(s) was/were determined by ICP-OES, ICP-MS, HPLC-ICP-MS and/or GC-MS.

### **Category Ⅲ:** scraped-off toy material

Tested Item(s)	Result (mg/kg)	100	MDL(mg/kg)	<u>Limit</u> (mg/kg)
Aluminium (Al)	153	(8)	50	70000
Antimony (Sb)	N.D.		5	560
Arsenic (As)	N.D.		5	47
Barium (Ba)	N.D.		50	18750
Boron (B)	N.D.		50	15000
Cadmium (Cd)	N.D.		1	17
Chromium (III) #1	N.D.		0.2	460
Chromium (VI)	N.D.	13	0.002	0.2
Cobalt (Co)	N.D.	(3)	5	130
Copper (Cu)	N.D.		50	7700
Lead (Pb)	N.D.		5	160
Manganese (Mn)	N.D.		50	15000
Mercury (Hg)	N.D.		5	94
Nickel (Ni)	N.D.		5	930
Selenium (Se)	N.D.		5	460
Strontium (Sr)	N.D.	73	50	56000
Tin (Sn) #2	N.D.	(6)	2	180000
Organic tin (TBT) #3	N.D.		0.05	12
Zinc (Zn)	N.D.		50	46000





Report No. SCL01I00408400701

Page 5 of 6

#### Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million
- Filter paper was used instead of membrane filter in lab testing.
- <sup>#1</sup> Trivalent chromium (Cr (III)) = Chromium (Cr) Hexavalent chromium (Cr (VI)), where the chromium content exceeded the limits of hexavalent chromium and/or trivalent chromium, then hexavalent chromium was analyzed by HPLC-ICP-MS and trivalent chromium content was calculated using the formula.
- <sup>#2</sup> Tin (Sn) content can be used for screen test for organic tins analysis to show compliance with the requirement of EN 71-3:2013+A1:2014.
- <sup>#3</sup> The migration of organic tin is expressed as tributyltin (TBT). where the tin content exceeded the limit of organic tin, ten organic tins listed in table were determined by GC-MS and the client should be noted there are other organic tins may be present in toy materials.

Organic tins tested under EN 71-3:2013+A1:2014	
Methyl tin (MeT)	)
Butyl tin (BuT)	
Dibutyl tin (DBT)	
Tributyl tin (TBT)	
Tetrabutyl tin (TeBT)	(8
n-Octyl tin (MOT)	
Di-n-octyl tin (DOT)	
Di-n-propyl tin (DProT)	
Diphenyl tin (DPhT)	)
Triphenyl tin (TPhT)	6

The test result(s) is(are) presented in reference to the result(s) that reported in SCL01I004084007.

**Tested Sample/Part Description** 

Blue ink

